



CARO-GUN 26

2020

CARO-GUN 26 is a low iron, high strength gun mix. This mix has excellent spalling resistance and is abrasion resistant and has very good resistance to thermal shock.

Maximum recommended service temperature..... 2600°F

Chemical Analysis (%)

Alumina (Al ₂ O ₃)	45.6
Silica (SiO ₂)	38.8
Iron (Fe ₂ O ₃)	2.3
Titania (TiO ₂)	2.4
Lime (CaO).....	7.9
Magnesia (MgO).....	0.2
Alkalies.....	0.2

Material required for install per cubic foot.....128 lb/ft³

Water Required for Gunning.....At Nozzle

Packaged in 75-pound bags, forty-eight bags per pallet (3600 pounds)