



CARO-GUN 28

2020

CARO-GUN 28 is an excellent 2800°F gunning mix. This material has high hot strength with minimal shrinkage.

Maximum recommended service temperature..... 2800°F

Chemical Analysis (%)

Alumina (Al ₂ O ₃)	48.4
Silica (SiO ₂)	40.1
Iron (Fe ₂ O ₃)	1.5
Titania (TiO ₂)	1.8
Lime (CaO).....	7.9
Magnesia (MgO).....	0.2
Alkalies.....	0.2

Material required for install per cubic foot.....130 lb/ft³

Water Required for Gunning.....At Nozzle

Packaged in 75-pound bags, forty-eight bags per pallet (3600 pounds)