



CARO-GUN 30

2020

CARO-GUN 30 is an abrasion resistant gunning mix. A low iron binder is used to increase its effectiveness under disintegrating action of carbon monoxide. This mix also has negligible shrinkage.

Maximum recommended service temperature..... 3000°F

Chemical Analysis (%)

Alumina (Al ₂ O ₃)	53.2
Silica (SiO ₂)	36.1
Iron (Fe ₂ O ₃)	1.7
Titania (TiO ₂)	2.3
Lime (CaO).....	6.3
Magnesia (MgO).....	0.2
Alkalies.....	0.2

Material required for install per cubic foot.....135 lb/ft³

Water Required for Gunning.....At Nozzle

Packaged in 75-pound bags, forty-eight bags per pallet (3600 pounds)