



**CAROBOND 90 W**

**2020**

**CAROBOND 90 W** is a high alumina, chemically bonded, wet mortar with extremely high refractoriness. Excellent strength and metal penetration resistance. Used for laying all types of high alumina brick. Excellent troweling characteristics.

Maximum recommended service temperature.....3200°F

**Chemical Analysis (%)**

Alumina (Al <sub>2</sub> O <sub>3</sub> ) .....	91.9
Silica (SiO <sub>2</sub> ) .....	1.2
Iron (Fe <sub>2</sub> O <sub>3</sub> ) .....	0.1
Alkalies (Na <sub>2</sub> O).....	0.1
Phosphorus Pentoxide (P <sub>2</sub> O <sub>5</sub> ) .....	6.59

**Material Required for Estimating:**

Mixing water required – Use as received

Storage Life 4-5 Months

Packaged in 60-pound pails, sixty pails per pallet (3600 pounds)